

JAZE MORTAR – HB

3-Component, High build, Light weight Epoxy Resin-based reinstatement Mortar with High Performance, Solvent-free, Abrasion & Chemical resistant.

Product Description:

JAZE MORTAR – HB is based on a high quality solvent-free epoxy resin system. The special lightweight filler is specifically designed to give excellent 'hanging' properties for vertical and overhead work. JCC MORTAR – HB is a 3-component material supplied in pre-weighed quantities ready for on-site mixing and use.

Uses:

For the fast and permanent reinstatement of concrete, particularly where resistance to chemicals is required. JAZE MORTAR – HB can be used for small, localized patch repairs and, because of its lightweight nature, is ideally suitable for use in vertical and overhead locations and for emergency repairs where fast strength gain is important. When properly compacted, the mortar is highly impermeable.

Advantages:

- Lightweight formulation enabling extra high build and thereby saving time and expense.
- Obviates the need for formwork.
- Early development of strength minimizes disruption.
- Highly resistant unaffected by a wide range of chemicals.
- Extremely low permeability.
- Equal to the strength of high quality concrete within 3 days.
- Pre-weighed components ensure consistency.
- Easy to mix and to apply.
- Solvent-free, odourless.
- Highly durable.
- Excellent abrasion and impact resistance.
- Non-shrink and non-skis finishes.
- Provides smooth surface.
- Excellent adhesion to sound concrete & masonry substrates.
- Excellent mechanical properties.
- High chemical resistant to most common chemical reagents.
- Formulated to be suitable for the Middle East Climates.

Technical Properties:

Appearance Pigmented free flowing liquid (mixed) **Specific Gravity** @20 °C **Solid Content** 100 % by weight @ 25 °C Pot-life 40 minutes. @ 25 °C **Full cure** 4-days Wet & dry thickness up to 20-mm Compressive Strength (N / mm²), BS 6319, Part 2. 40 (after 28 days) (N / mm²), BS 6319, Part 3 Flexural strength 15 (after 28 days) (N / mm²), BS 6319, Part 7. **Tensile Strength** 7 (after 28 days) Bond Strength to concrete (N/mm²), ASTM C-882 **Abrasion resistance** 60 mg as per as Taber Abrasive, 1000

grams / 1000 revolution.

For Further Information Contact: www.jcc-sa.com



Chemical Resistance

JAZE MORTAR - HB has been tested for chemical resistance to a comprehensive range of industrial & domestic chemicals. After constant immersion for 90-days @ 35 °C in accordance with ASTM D-2240 (Shore D hardness), the results are:

	<u>Acids</u>			<u>Alkalis</u>		
	Hydrochloric	25 %	Excellent	Sodium hydroxide	25 %	Excellent
	Sulfuric	10 %	Excellent	Sodium Carbonate	25 %	excellent
	Nitric	10 %	Good	Ammonia	10 %	Excellent
	Acetic	25 %	Excellent	Potassium Hydroxide	25 %	Excellent
	Lactic	10 %	Excellent	Sodium Hypochlorite	15 %	Excellent
	Citric	10 %	Excellent			
Solvents & Oils						
	Ethanol		Excellent	Soya Bean Oil		Excellent
Ethyl Glycol		Excellent	Vegetable Oil		Excellent	
	White spirit		Excellent	Detergent		Excellent
	Petrol & Diese	el Oil	Excellent	Fat		Excellent
	Coconut oil		Excellent	Milk		Excellent
	Cotton Seed Oil		Excellent	Pine Oil		Excellent
Soya Bean Oil		Excellent	Linseed Oil		Excellent	
	Silicates		Excellent	Water		Excellent
	For Specific Chemical reagent, please ask for technical support.					

About 2 m² / Kg / mm thickness Coverage

Guide for Applications:

Surface Preparation:

All surfaces shall be sound, clean free from dust, grease & oils, curing agents & mould releasing agents or other materials may affect the bond of the product and the substrates. Steel or metal surfaces should be free from rust, scale or other contaminants.

JAZE PRIME- EP 10 shall be used prior to the application (See separate data Sheet)

Mixing:

Stir each component JAZE MORTAR - HB well before mixing. Pour Component A into clean vessel, then pour Component B and mix well till homogeneity, then add Component C while mixing and continue mixing till homogenous consistency, color & self-levelling free from lumps is achieved. Electric drill with low speed (400-500 rpm) is recommended.

Application:

Apply the mixed materials onto prepared & primed substrates while the primer is still tacky (wet on wet) in the required thickness in single application. After laying the mixed material, it shall be tamped with a wooden float and levelling with screeding bar to ensure full compacting.

Final finish trowel by stainless steel float to achieve the recommended finish.

Packaging:

JAZE MORTAR – HB is supplied in 8 -Kg and 16 kg kits.

Storage & Shelf-life:

JAZE MORTAR - HB shall be stored in normal conditions away from any extreme temperatures, Shelf – life is 12 months if stored properly.

Health & Safety:

- JAZE MORTAR HB is non-toxic, non-corrosive, and non-dangerous.
- For Ecology: Do not dispose directly to water or soil. Mix Component A with Component B and wait till hardening, then burry in landfill in accordance with the local regulations.
- Splashes on skin will be washed with water and soap.

JCC CONSTRUCTION CHEMICALS

The information herein is general information to assist our customers in determining whether our products are suitable for their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers should inspect and test our products before use to satisfy themselves as to the content and suitability for the application they intend to use our products for.

JCC endeavors to ensure that any advice, recommendation, specification of information in accurate and correct manner.