

JAZECOAT – EP 402

2-Component, Non-toxic, High Performance, Solvent-free, Chemical resistant Epoxy Resin-based Protective Coating Suitable to be in Contact with Drinking Water

Product Description

JAZECOAT – EP402 is 2-component, solvent-free (100 % solid), non-toxic, epoxy resin-based high- build, high performance, chemical resistant protective coating that is suitable to be in contact with drinking water. It will provide after application and curing a durable protective, sealing & decorative film with an excellent abrasion & chemical resistance that is easy to-clean surface finish. It is based on selected epoxy resin & special hardener that resist amine blush. The product is available in white, blue colours or any colour upon request.

Uses

JAZECOAT– EP402 is formulated to provide continuous protective coating having slip resistant, abrasion resistant, chemical resistant properties. It formulated for lining and waterproofing potable water retaining structures and surfaces that to be in contact with foodstuffs. It suitable for areas where thick film is required such as:

- Water tanks & reservoirs and silos.
- Food processing areas.
- Dairies & kitchens.
- Soft-drink bottling.
- Storage tanks.
- Laboratories.
- Clean rooms
- All similar work

Advantages

- Easy to apply by suitable brush or roller.
- Solvent-free (100 % Solid), odourless.
- Non-toxic and suitable to be in contact with drinking water and foodstuff.
- Highly durable and corrosion resistance.
- Excellent abrasion and impact resistance.
- Hygienic, impervious.
- Provides easily cleaned surfaces.
- Excellent adhesion to sound concrete & masonry substrates.
- High chemical resistant to most common chemical reagents.
- Can be used with glass fiber to provide more mechanical properties.
- Formulated to be suitable for the Middle East Climates.

Standards

JAZECOAT- EP 402 complies with ASTM C- 881, Type III, Grade 2, and Class B & C

Technical Properties

Appearance	Pigmented free flowing liquid
Specific Gravity @20 °C	1.50
Solid Content	100 % by weight
Application temperature	5 – 35 °C.
Time between recoating	12 – 24-hours.
Pot-life @ 25 °C	50 minutes.
Full cure @ 25 °C	7-days
Wet & dry film thickness	200 microns per coat
Abrasion resistance	70 mg as per as Taber Abrasive, 1000 grams / 1000 revolution.
Bond Strength	2.5 N / mm ² .



Chemical Resistance

JAZECOAT – EP 402 has been tested for chemical resistance to a comprehensive range of industrial & domestic chemicals. After constant immersion for 90-days @ 35 °C in accordance with ASTM D-2240 (Shore D hardness), the results are:

Acids

Hydrochloric	25 %	Excellent
Sulfuric	25 %	Excellent
Nitric	25 %	Good
Acetic	10 %	Excellent
Lactic	10 %	Excellent
Citric	10 %	Excellent

Alkalis

Sodium hydroxide	25 %	Excellent
Sodium Carbonate	25 %	excellent
Ammonia	20 %	Excellent
Potassium Hydroxide	25 %	Excellent
Sodium Hypochlorite	15 %	Excellent

Solvents & Oils

Ethanol	Excellent	Soya Bean Oil	Excellent
Ethyl Glycol	Excellent	Vegetable Oil	Excellent
White spirit	Excellent	Detergent	Excellent
Petrol & Diesel Oil	Excellent	Fat	Excellent
Coconut oil	Excellent	Milk	Excellent
Soya Bean Oil	Excellent	Linseed Oil	Excellent
Silicates	Excellent	Water	Excellent

For Specific Chemical reagent, please ask for technical support.

Coverage

About 4 m² per Kg per 200 microns.
Two coats are recommended.

Guide for Applications

Surface Preparation

All surfaces shall be sound, clean free from dust, grease & oils, curing agents & mould releasing agents or other materials may affect the bond of the product and the substrates. Steel or metal surfaces should be free from rust, scale or other contaminants.

Priming

EAMIPRIME- EP 10 can be used prior to the application (See separate data Sheet) to get the optimum properties.

Mixing

Stir each component of JAZECOAT –EP402 well before mixing. Pour Component A into the Component B and mix well for 2 -5minutes until uniform consistency & colour is achieved.

Application

Apply the mixed materials of JAZECOAT–EP402 onto prepared & primed substrates using suitable brush, roller or airless spray method for large areas

Apply the second coat after application of the first coat with 12 hours.

Packaging

JAZECOAT – EP402 is supplied in 6 –Kg or 18-Kg Kits.

Storage & Shelf-life

JAZECOAT– EP402 shall be stored in normal conditions away from any extreme temperatures, Shelf – life is 24 months if stored properly.

Health & Safety

- JAZECOAT – EP402 non-toxic, non-corrosive, and non-dangerous.
- For Ecology: Do not dispose directly to water or soil. Mix Component A with Component B and wait till hardening, then bury in landfill in accordance with the local regulations.
- Splashes on skin will be washed with water and soap.

JCC CONSTRUCTION CHEMICALS

The information herein is general information to assist our customers in determining whether our products are suitable for their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers should inspect and test our products before use to satisfy themselves as to the content and suitability for the application they intend to use our products for.

JCC endeavors to ensure that any advice, recommendation, specification of information in accurate and correct manner.